What is claimed is:

1.   A propylene resin composition comprising:

(A) a crystalline propylene block copolymer in an amount of 89 to 30% by weight, which has a 23°C n-decane-soluble component content of 15 to 35% by weight, said soluble component having an intrinsic viscosity $[\eta]a$, as measured in decalin at 135°C, of not less than 1 dl/g and less than 5 dl/g, has a melt flow rate (MFR, 230°C, load of 2160 g), as measured by the method of ASTM D 1238, of 10 to 150 g/10min, and has an isotactic pentad fraction of a polypropylene homopolymer portion, as measured by ^{13}C-NMR, of not less than 0.97,

(B) a crystalline propylene block copolymer in an amount of 5 to 25% by weight, which has a 23°C n-decane-soluble component content of 15 to 35% by weight, said soluble component having an intrinsic viscosity $[\eta]b$, as measured in decalin at 135°C, of 5 to 10 dl/g, has a melt flow rate (MFR, 230°C, load of 2160 g), as measured by the method of ASTM D 1238, of 1 to 35 g/10min, and has an isotactic pentad fraction of a polypropylene homopolymer portion, as measured by ^{13}C-NMR, of not less than 0.97,

(C) an elastomeric polymer in an amount of 1 to 20% by weight, which has a melt flow rate (MFR, 230°C, load of 2160 g) of 0.5 to 30 g/10min, and

SF-999PCT

(D) an inorganic filler in an amount of 5 to 25% by

weight,

with the proviso that the total amount of the

components (A) to (D) is 100% by weight.

5

2.   The propylene resin composition as claimed in

claim 1, wherein the intrinsic viscosity $[\eta]e$ of the

elastomeric polymer (C) and the intrinsic viscosity $[\eta]a$

of the n-decane-soluble component of the crystalline

10   propylene block copolymer (A) have a relationship of the

following formula (1):

$$0.5 \leq [\eta]e/[\eta]a \leq 2 \qquad (1).$$